


MOUTH-BLOWN RESTORATION WINDOW GLASS

Old World Colonial™


Authentic! Hand-made in Europe the way it has been for hundreds of years, this mouth-blown glass is produced by master craftsmen. This glass is a beautiful balance of clarity and movement. It is exactly what you want if your restoration job calls for 100% authenticity when replacing blown glass from the pre-1900's. This exquisite glass is available in three categories: P-1, Light Restoration Window Glass; P-2, Medium with Cords; and RM, Heavy with Reams.



DRAWN RESTORATION WINDOW GLASS

Restover®

A distinctive machine drawn fire polished glass which adds beauty and elegance to any light restoration project where early 1900's authenticity is required. It features a subtle wave and no seeds or defects. Available in 1/8" and 3/16" (temperable) thicknesses. Large sheet sizes offer extended application possibilities and utilization optimization.



DRAWN AUTHENTIC RESTORATION WINDOW GLASS

ReNova™

ReNova™ is the most authentic looking machine drawn restoration window glass on the market today. Produced specially for Hollander Glass and Bevel King Door and Glass Company, this fire-polished glass is a near perfect match to any fully mouth blown window glass that you will find. It exhibits a beautifully fluid, crystal clear waviness, is temperable, available in high-yield sizes, all at a more affordable price!



HEAT TREATED RESTORATION WINDOW GLASS

Retroverre™

When period authenticity is not a requirement, yet the "old world" look is desired and economy is a consideration, **Retroverre™** is a clear choice. Made from a proprietary process that infuses tiny pits in the surface of a highly polished glass, **Retroverre™** conveys the illusion of old glass. **Retroverre™** offers the highest yield with its non directional distortion with the added advantage that the distortion is noticeable even in small pieces. Ideal for kitchen cabinet glass, old clocks, furniture, and lighting fixtures. Available in 3mm (1/8") thickness, **Retroverre™** can only be tempered in special circumstances by the manufacturer.




MOUTH-BLOWN AND MACHINE DRAWN

Restoration Window Glass Comparison Table

Brand	Old World Colonial™	Old World Colonial™	Old World Colonial™	Restover™	Goethe	Renova™	Retroverre™
Description	P1 Light	P2 Medium	RM Reamy	Drawn light	Drawn light	Drawn medium	Heat treated medium
Stock #	RG MAICO	RG MA2CO	KR IRM	RG 0189	RG 01895	RG 0189R	RG 2860
Manufacturing Method	Mouthblown	Mouthblown	Mouthblown	Vertical Draw	Vertical Draw	Vertical Draw	Heat treated
Referred to as	Cylinder	Cylinder	Cylinder	Machine Drawn	Machine Drawn	Machine Drawn	Neorestoration
Also referred to as	Light	Medium	Heavy	Light	Light	Medium	Medium
Original time period	Pre-1900's	Pre-1900's	Pre-1900's	1900 to 1950	1900 to 1950	Simulates Pre-1900's	Simulates old glass
Thickness	2-3mm or 1/8" some variation	2-3mm or 1/8" some variation	2-3mm or 1/8" some variation	2.75±0.25mm or 1/8" consistent	4.5±0.50mm or 3/16" consistent	3.6±0.50mm or 1/8" consistent	3mm or 1/8" consistent
Dimensions	up to 36" x 36" some variation	up to 36" x 36" some variation	up to 36" x 36" some variation	40" x 60" & 59" x 63" consistent	40" x 60" & 59" x 63" & up to 63" x 83" consistent	41.7" x 61.4" & 61.4" x 61.4" & 84.7" x 61.4" consistent	28" x 60" consistent
Waviness in glass	Moderate	Moderate	Moderate	Light	Light	Moderate like mouthblown	Moderate
Surface Distortion	Clear	Clear	Clear	Fire-polished	Fire-polished	Fire-polished	Pitted fire-polished
Draw or roller lines	No	No	No	No	No	No	No
Cords and reams	No	Cords	Reams	No	No	No	Pits
Seeds	Occasionally	Occasionally	Occasionally	No	No	No	Pits
Bubbles	Occasionally	Occasionally	Occasionally	No	No	No	No
Other defects	Occasionally	Occasionally	Occasionally	No	No	Occasionally/ slight	Pits
Flatness	Minor variations	Minor variations	Minor variations	Very good	Very good	Very good	Good
Can it be tempered?	No	No	No	Check with your temperer	Yes	Yes	Limited

F.O.B. our warehouse. Additional freight and boxing charges are applicable.



www.hollanderglass.com

Hollander Glass Central, Inc.
 phone: (630) 350-2063
 fax: (630) 350-2366
 (800) 323-4293
central@hollanderglass.com

Hollander Glass East, Inc.
 phone: (732) 346-1211
 fax: (732) 346-1711
 (800) 221-6207
east@hollanderglass.com

Hollander Glass Southwest, Inc.
 phone: (602) 278-9833
 fax: (602) 278-9843
 (877) 278-9833
sw@hollanderglass.com

Hollander Glass Texas, Inc.
 phone: (713) 460-0045
 fax: (713) 462-3646
 (800) 421-0449
texas@hollanderglass.com

Bevel King™ Door & Glass
 phone: (678) 904-1136
 fax: (678) 904-3360
 (877) 238-5464
atlanta@bevelkingdoors.com